





## **DESCRIPTION**

Position	Product	Process	Thickness (nominal)	Weight
T COLLIGIT	TON	110000	) <sub>Z</sub> mm	kg/m²
Pilkington Insuligh	<b>t</b> ™ Therm Triple	arthics arthic	A THE PARTY OF THE	
Glass 1	Pilkington <b>Optiwhite</b> ™	Annealed	4.0	201772
Cavity 1	Argon (90%)		14.0	7
Glass 2	Pilkington <b>K Glass™</b> S	Annealed	4.0	pl.
Cavity 2	Argon (90%)	300 300 300 100 100 100 100 100 100 100	14.0	100°C
Glass 3	Pilkington <b>K Glass™</b> S	Annealed	4.0	Valley.
Product Code	4w-14Ar-KS4-14Ar-KS4		40.0	30.00

## **PERFORMANCE**

Light	
Transmittance	LT 71%
ACTOR-	UV % 27%
Reflectance Out	LR out 15%
Reflectance In	LR in 16%
Performance Code	
U <sub>g</sub> -value/Light/Energy	0.7 / 71 / 64
Ra	Pillan 98
The values of some of chara stands for No Performance I	cteristics are displayed as NPD. This Determined.

Energy		
Direct Transmittance	ET	50%
Reflectance	ER	26%
Absorptance	EA	24%
Total Transmittance	g	64%
Shading Coefficient Total		0.74
Shading Coefficient Shor	twave	0.57
Sound Reduction	R <sub>w</sub> (C;C <sub>tr</sub> ) dB	32 (-1; -4)
Thermal Transmittance	W/m <sup>2</sup> K	0.7

Additional Values			
Bullet Resistance	NPD	Burglar Resistance	NPD+NPD+NPD
Explosion Resistance	NPD	External Fire Performance	NPD
Load Resistance (mm)	4+4+4	Pendulum Body Impact Resistance	NPD
Reaction to Fire	NPD	Resistance to Fire	NPD
Resistance to Temperature Differentials (K)	40+40+40		

Pilkington Spectrum allows you to combine a wide range of products available from Pilkington and determine their key properties such as light transmittance, g value and U value. The program includes restrictions that prevent some combinations being selected that may be considered unwise or impractical. Even with these restrictions, it is still possible to create product combinations that may not be available from your supplier. Please check with your supplier that your chosen product combination is possible, available in the sizes required and in a timescale appropriate to your project. Furthermore, it is essential that you check that your product combination is appropriate for satisfying local, regional, national and other project-specific requirements.

Calculations are made according to EN standards 410 and 673/12898









