





DESCRIPTION

Position	Product	Process	Thickness (nominal)	Weight kg/m²
Pilkington Insuligh	t ™ Therm Triple	Age.	ia.	11110
Glass 1	Pilkington Optiwhite ™	Annealed	4.0	
Cavity 1	Argon (90%)	(69)	12.0	
Glass 2	Pilkington K Glass™ S	Annealed	4.0	
Cavity 2	Argon (90%)	WING WIN	12.0	
Glass 3	Pilkington K Glass™ S	Annealed	4.0	16.00
Product Code	4w-12Ar-KS4-12Ar-KS4		36.0	30.00

PERFORMANCE

Light	
Transmittance	LT 71%
A GION	UV % 27%
Reflectance Out	LR out 15%
Reflectance In	LR in 16%
Performance Code	
U _g -value/Light/Energy	0.8 / 71 / 64
Ra	98
The values of some of chara stands for No Performance I	acteristics are displayed as NPD. This Determined.

Energy		
Direct Transmittance		ET 50%
Reflectance	A GIV	ER 26%
Absorptance		EA 24%
Total Transmittance		g 64%
Shading Coefficient Total		0.74
Shading Coefficient Short	wave	0.57
Sound Reduction	$R_{w}(C;C_{tr}) dB$	32 (-1; -5)
Thermal Transmittance	W/m ² K	0.8

Additional Values				
Bullet Resistance	NPD	Burglar Resistance		NPD+NPD+NPD
Explosion Resistance	NPD	External Fire Performance		NPD
Load Resistance (mm)	4+4+4	Pendulum Body Impac	t Resistance	NPD
Reaction to Fire	NPD	Resistance to Fire		NPD
Resistance to Temperature Differentials (K)	40+40+40		69)	

Pilkington Spectrum allows you to combine a wide range of products available from Pilkington and determine their key properties such as light transmittance, g value and U value. The program includes restrictions that prevent some combinations being selected that may be considered unwise or impractical. Even with these restrictions, it is still possible to create product combinations that may not be available from your supplier. Please check with your supplier that your chosen product combination is possible, available in the sizes required and in a timescale appropriate to your project. Furthermore, it is essential that you check that your product combination is appropriate for satisfying local, regional, national and other project-specific requirements.

Calculations are made according to EN standards 410 and 673/12898









